

View Article Online View Journal

# Energy & Environmental Science

# Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: H. Zhu, L. Gu, D. Yu, Y. Sun, M. Wan, M. Zhang, L. Wang, L. Wang, W. Wu, J. Yao, M. Du and S. Guo, *Energy Environ. Sci.*, 2016, DOI: 10.1039/C6EE03054H.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the **author guidelines**.

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard <u>Terms & Conditions</u> and the ethical guidelines, outlined in our <u>author and reviewer resource centre</u>, still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.



rsc.li/ees

YAL SOCIETY

nergy & Environmental Science Accepted Manuscript

### Journal Name

## ARTICLE

Received 00th January 20xx, Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

# The Marriage and Integration of Nanostructures with Different Dimensions for Synergistic Electrocatalysis

Han Zhu<sup>1</sup>, Li Gu<sup>1</sup>, Danni Yu<sup>1</sup>, Yingjun Sun<sup>2,3</sup>, Meng Wan<sup>1</sup>, Ming Zhang<sup>1</sup>, Lei Wang,<sup>3</sup> Lina Wang<sup>1</sup>, Weiwei Wu<sup>1</sup>, Juming Yao<sup>1</sup>, Mingliang Du<sup>1\*</sup> and Shaojun Guo<sup>2, 4,5\*</sup>

The search for new ways to make inexpensive and efficient electrocatalysts to replace precious-metal platinum catalysts for oxygen reduction and water splitting is still a great challenge. Here, we report a facile and effective strategy for the rational design and construction of three-dimensional (3D) architectures for superior electrocatalysis through the integration of one-dimensional (1D) electrospun carbon nanofibers (CNFs), 1D carbon nanotubes (CNTs) and 0D oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> nanoparticles (NPs). The rationale behind the marriage and integration of nanostructures with different dimensions presented in this work is that during heat treatment, the *in situ*-produced CoMnO NPs are partly reduced to Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> by a carbon precursor with an amount of metallic Mn<sub>3</sub>Co<sub>7</sub> formed at the interface between the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs and carbon, which can act as the catalysts for the growth of 3D CNT forests. The 3D CoMnO@CNTs/CNFs architectures exhibit superior electrocatalytic activity and stability for the oxygen reduction, oxygen evolution and hydrogen evolution reactions. The remarkable electrochemical properties are mainly attributed to the synergistic effects from the engineering of oxygen-deficient binary CoMn oxide NPs with exposed active sites and 3D hierarchical porous structures consisting of branched CNTs and interconnected CNFs. The present work demonstrates the first example of integrating multiple active catalytic centers onto/into 3D architectures for developing highly efficient non-precious metal nanocatalysts for electrochemical energy devices.

#### **Broader context**

The electrocatalytic water splitting is a practical and environmentally friendly approach to generate hydrogen for powering fuel cells. On the journey to pursue the replacement of noble metals in electrocatalysts with earth-abundant elements, the carbon-based nanomaterials incorporated with transition metals have attracted growing attention. Hierarchical carbon nanomaterials are highly suitable as electrocatalysts and electrocatalyst supports in electrocatlytic conversion devices. The intrinsic kinetics of an electrocatalyst are associated with the nanostructure of the active phase and the support, while the overall properties are also affected by the mesostructure. Here, we provide a new design of three-dimensional architectures for superior electrocatalysis through the integration of electrospun carbon nanofibers (CNFs), carbon nanotubes (CNTs) and oxygen-deficient CoMnO nanoparticles. This strategy involves in a new transition metal oxides catalysts for CNTs growth using polymer nanofiber as carbon resources. The morphology, naostructure, crystal phase and electrocatalytic activity of the CoMnO@CNTs/CNFs architecture can be controlled by adjusting the graphitization process and conditions. The remarkable electrochemical properties are mainly attributed to the synergistic effects obtained from the engineering of oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> with exposed active sites and the 3D hierarchical porous structure, which consists of branched CNTs and interconnected CNFs. This work demonstrates a novel integration-and-marriage concept for developing superior catalysts for electrochemical energy devices.

<sup>1</sup>College of Materials and Textiles, Key Laboratory of Advanced Textile Materials and Manufacturing Technology of the Ministry of Education, Zhejiang Sci-Tech University, 310018, P. R. China

<sup>2</sup>Department of Materials Science and Engineering, College of Engineering, Peking University, 100871, P. R. China

<sup>3</sup>College of Chemistry and Molecular Engineering, Qingdao University of Science and Technology, Qingdao 266042, P.R. China

<sup>4</sup>BIC-ESAT, College of Engineering, Peking University, Beijing 100871, China.

<sup>5</sup>Key Laboratory of Theory and Technology of Advanced Batteries Materials, College of Engineering, Pering University, Beijing 100871, China.

E-mail: (<u>du@zstu.edu.cn</u>; <u>guosj@pku.edu.cn</u>)

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

Introduction

The rise of clean and renewable hydrogen offers mankind a promising opportunity to overcome our reliance on fossil fuels and to address the challenges of global warming, environment pollution and the energy crisis.<sup>[1-3]</sup> Electrocatalytic water splitting through the two half-reactions, hydrogen evolution reaction (HER) and oxygen evolution reaction (OER), is a clean and sustainable approach to generate molecular hydrogen (H<sub>2</sub>).<sup>[4-6]</sup> In addition, hydrogen is supposedly an economic fuel

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

used in electrochemical cells for electric devices, such as fuel cells and metal-air batteries.<sup>[7,8]</sup> Oxygen reduction reaction (ORR) and OER are the key reactions for the important energy conversion and storage processes in electrochemical devices.<sup>[9]</sup> These important electrochemical reaction processes need effective catalysts to minimize reaction kinetic barriers, expedite the reactions, reduce the overpotential, and thus improve the energy conversion efficiency. To achieve these targets, substantial efforts have been devoted to designing low-cost earth-abundant transition metal-based electrocatalysts to replace the state-of-the-art Pt and IrO2 catalysts for ORR, HER and OER.<sup>[9-11]</sup> A series of affordable, sustainable, and efficient catalysts, such as transition metal sulfides<sup>[12]</sup>, carbides<sup>[13]</sup>, nitrides<sup>[14]</sup>, and phosphides<sup>[15]</sup> show great potential for enhancing ORR, HER and OER catalysis, but their performance is still far from that of the commercial Pt/C catalyst. This is because only controlling the chemical composition of the transition metal-based materials cannot provide enough electrocatalytic active centers for achieving highly efficient nanoelectrocatalyts.

One of the most promising ways for addressing this issue is by controlling three-dimensional (3D) nanoarchitectures using hierarchical meso- and/or macro-porosity and adequate catalytic centers to improve the kinetics of the catalysis  $\operatorname{process.}^{[16,17]}$  Oxygen vacancies in nanocrystals were shown to be the effective electrocatalytic centers due to their good/optimized affinity towards O<sub>2</sub>.<sup>[18-20]</sup> However, achieving carbon nanotubes/transition metal oxide-based 3D architectures with an adequate amount of oxygen vacancies that function as effective active centers has received very limited attention. Herein, we report the first example of attaching carbon nanotubes/oxygen-deficient CoMnO nanoparticle (NP) hybrids onto carbon nanofibers (CNFs) to form 3D nanoarchitectures for boosting ORR, HER and OER electrocatalysis. The unique part of the synthesis presented is that the CoMnO NPs were gradually reduced from CoMn<sub>2</sub>O<sub>4</sub> crystals to oxygen-deficient Co2Mn3O8 NPs with metallic Co<sub>3</sub>Mn<sub>7</sub> surfaces during the heat treatment, and the formed oxygen-deficient Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs were used as catalysts to grow the branched CNTs, which then formed the 3D nanoarchitectures.

We found that the oxygen-deficient Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs with metallic Co<sub>3</sub>Mn<sub>7</sub> surfaces are encapsulated at the tips of CNTs and in the channels of the porous graphitic CNFs matrix. By integrating the catalytically active  $Co_2Mn_3O_8$  NPs, a high nitrogen doping and 3D CNTs, the 3D architectures exhibit superior electrocatalytic activity and stability for ORR with onset and half-wave potentials of 0.87 and 0.81 V vs. reversible hydrogen electrode (RHE), HER with a low overpotential of 175 mV vs. RHE at a current density of 10 mA cm<sup>-2</sup> and a Tafel slope of 101 mV decade<sup>-1</sup>, and OER with an overpotential of 370 mV vs. RHE at 10 mA cm<sup>-2</sup> and a Tafel slope of 66 mV decade<sup>-1</sup>, which are among the best results reported to date for multifunctional catalysts. These remarkable electrochemical properties are mainly attributed to the synergistic effects from the engineering of oxygendeficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs with exposed active sites and 3D hierarchical porous structures consisting of branched CNTs and interconnected CNFs. The Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs exhibit remarkable stability under continuous operation for 10 h during the electrocatalysis process. This facile strategy for

the marriage and integration of 1D CNTs, 1D CNFs and 0D oxygen-deficient  $Mn_3Co_7\text{-}Co_2Mn_3O_8$  NPs provides new prospects in the development of highly efficient multifunctional nanomaterials for electrochemical energy devices.

#### **Results and discussion**

A two-step strategy was used to fabricate the 3D oxygendeficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs architecture. In the first step, polyacrylonitrile (PAN) nanofibers were prepared via electrospinning the mixture containing a certain amount of Co(NO<sub>3</sub>)<sub>2</sub> and Mn(Ac)<sub>2</sub>. As-made Co-Mn/PAN nanofibers exhibit the fiber morphology with a uniform diameter of approximately 560 nm (Figure S1). After pre-oxidation at 400 °C for 5 h under air condition and thermal treatment at 1000 °C for 6 h in an inert atmosphere (Ar/NH<sub>3</sub>), the Co-Mn/PAN polymer nanofibers were converted into 3D nanoarchitectures containing porous CNFs, binary cobalt and manganese oxide NPs, and branched CNT forests. Large amounts of CNTs spring up densely from the CNFs, and are vertically grown around the CNFs to form the novel 3D nanoarchitectures (Figure 1a). The binary CoMnO NPs either exist at the tips of the CNTs or are enclosed inside the CNTs, where the NPs are in intimate contact with the carbon shell (Figure 1b).



**Figure 1** (a, b) FE-SEM and (c, d) TEM images of 3D oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$  architecture. (e) High-magnification TEM image of the porous graphitic CNFs matrix. (f) High-resolution TEM (HRTEM) image of the fullerene-like graphitic carbon pores catalyzed by the COMnO NPs, and the inset is the HRTEM image of the graphene walls. (g) TEM image of the CNTs and (h) single CNTs, with each NT tip containing one COMnO NP. (i) HRTEM image of the CNTs, and the inset is the HRTEM image of the CNTs, and the inset is the HRTEM image of the CNTs, and the inset is the HRTEM image of the CNTs, and the inset is the HRTEM image of the CNTs, with each NT tip containing one COMnO NP. (i) HRTEM image of the CNTs, and the inset is the HRTEM image of the graphene walls. (j) HRTEM image of the CNTs.

Unlike the chemical vapor deposition (CVD) method for the growth of CNTs in a vapor-liquid-solid process, the CoMnO NPs were first formed inside the nanofibers during the oxidation process at 400 °C. And then the as-formed CoMnO NPs catalyze the conversion from the amorphous organic nanofibers to the graphitic porous CNFs along with the growth of CNTs. Figure 1c and 1d show the hierarchical structure of the porous CNFs with CoMnO@CNTs forests. We found that in addition to the CoMnO NPs encapsulated in CNTs, there are certain amounts of CoMnO NPs embedded in the CNFs. The

DOI: 10.1039/C6EE03054H

Journal Name

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

#### Journal Name

encapsulated CoMnO NPs can catalyze the conversion from amorphous carbon to graphitic carbon, which leads to the formation of porous graphitic CNFs. Because of the strong catalytic effect of the CoMnO NPs, the CNFs matrix consists of a large amount of fullerene-like graphitic carbon pores catalyzed by the CoMnO NPs (Figure 1e). The fullerene-like pores clearly exhibit well-ordered graphene layers with a dspacing of 3.4 Å, which corresponds to the (002) planes of carbon (Figure 1f). The graphitic wall of the fullerene-like pore ranges between approximately 10 to 40 graphene layers. The graphene layers not only hold the NPs but also improve the electrical conductivity of the carbon matrix. Figure 1g and 1h show the TEM images of CNTs catalyzed by the CoMnO NPs. Most of the CoMnO NPs are located at the tips of the CNTs, and the length of the CNTs ranges from 0.5 µm to 5 µm. The as-formed CNTs are multi-walled with a diameter of approximately 10-50 nm and a wall thickness of 5-15 nm (Figure 1g-i). From Figure 1i, the graphene planes are parallel to the tube axis with a layer distance of 3.40 Å. At the tips of the multi-walled CNTs (MWCNTs) (Figure 1j), the CoMnO NPs exhibit a d-spacing of 2.86 Å, which corresponds to the [200] plane of Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs.



Figure 2 (a) HAADF-STEM image of the oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$ . (b) STEM-EDX mapping image of the selected area of  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$ . (c) The overlay between Co and Mn in the STEM-EDX mapping area. (d) HRTEM image of a single oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8$  NP at the tip of a CNT. (e) Linescan EDX spectra of the oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$ , and the inset in Figure 2e is the line-scan area. (f) XRD pattern of the  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$  architecture.

We further employ high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM)-energydispersive X-ray spectroscopy (EDX) mapping technique to investigate the elemental distribution of the 3D CoMnO@CNTs/CNFs architecture. Uniform and distinct MWCNTs along with the CoMnO NPs are clearly observed (Figure 2a and 2b). There are strong K-edge signals of carbon and nitrogen elements in the nanotubes, which confirms the formation of N-doped CNTs. Furthermore, the signals of carbon and nitrogen appear around the NP area, indicating that the CoMnO NPs were encapsulated into the CNTs. The NPs have strong K-edge signals of cobalt, manganese and oxygen elements, confirming the successful formation of binary CoMnO NPs. Furthermore, there are signals of manganese beyond the CoMnO boundary, which is attributed to the metallic manganese on the surface of the CoMnO NPs (Figure 2c). The HRTEM image of the CoMnO NPs at the tip of CoMnO@CNTs also provides the evidence of the formation of metallic manganese at the interface between the surfaces of CoMnO NPs and the surrounding fullerene carbon layers. These results indicate that the binary CoMn oxide NPs encapsulated into the CNTs are not single-phase NPs, and an amount of metallic Mn is formed around the CoMnO NPs.

As shown in Figure 2d, the marked area of the CoMnO NP exhibits distinct lattice fringes with interlayer distances of 2.11 Å, corresponding to the (122) plane of  $Co_2Mn_3O_8$  NPs. There is also another lattice fringe outside the CoMnO with an interlayer distance of 2.49 Å, which belongs to the metallic Mn<sub>3</sub>Co<sub>7</sub>. This is because the CoMnO NPs, directly in contact with carbon, were partly reduced to Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> with an amount of metallic Mn<sub>3</sub>Co<sub>7</sub> formed at the interface between the Co2Mn3O8 NPs and carbon. The line-scan STEM-EDS spectra provide more evidence of the formation of CoMnO NPs. As revealed in Figure 2h, the K-edge signals of the Co, Mn and O elements are mainly centered at the bright spot, which corresponds to the CoMnO NPs. The surrounding of the CoMnO nanoparticles exhibits an even distribution of carbon and nitrogen signals, which indicates the successfully formation of N-doped CNTs.

The crystalline structure, surface chemical state and chemical composition of the CoMnO@CNTs/CNFs were further investigated by powder X-ray diffraction (XRD) and X-ray photoelectron spectroscopy (XPS) measurements. The XRD pattern of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared at 1000 °C exhibits a broad band at 25.2 °, which corresponds to the (002) plane of the graphitic carbon of CNF catalyzed by Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs (Figure 2f).<sup>[21]</sup> A sharp and distinct peak located at 26.5  $^\circ$  corresponds to the CNTs and indicates the high degree of graphitic carbon.<sup>[22]</sup> A series of other XRD peaks located at 32.7 °, 44.4 ° and 48.5 ° are characteristic of the (103), (122) and (220) planes of Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> nanocrystals (labeled as \*, JPCDS card #30-0446).<sup>[23]</sup> Furthermore, some peaks emerged at 35.4 °, 41.0 °, 41.8 °, 43.7 °, 48.4 °, 51.4 ° and 59.0°, which correspond to the Mn<sub>3</sub>Co<sub>7</sub> nanocrystals (labeled as #, PDF#18-0407); this further confirms the formation of the metallic Mn<sub>3</sub>Co<sub>7</sub> phase.<sup>[24]</sup>

XRD patterns of the CoMnO@CNTs/CNFs heated at different temperatures (400, 600 and 800 °C) were obtained to further investigate the structure of the 3D CoMnO@CNTs/CNFs architectures (Figure 3a). The XRD pattern of the CoMnO@CNTs/CNFs prepared at 400 °C (Figure 3a) shows a peak at approximately 24.2 °, which is attributed to the (002) plane of carbon. The other peaks at 29.8°, 43.9°, 64.4 ° and 77.4 °, respectively, can be indexed to the (202), (400), (440), (622) planes of spinel-type (Co,Mn)(Mn,Co)<sub>2</sub>O<sub>4</sub> crystals (PDF#18-0409).<sup>[23]</sup> Therefore, at the initial stage of 400 °C, the CoMnO NPs are mainly spinel-type CoMn<sub>2</sub>O<sub>4</sub> crystals formed on CNFs (Figure 3a). The XRD pattern of the CoMnO@CNTs/CNFs prepared at 600 °C indicate that the CoMn<sub>2</sub>O<sub>4</sub> and Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs co-exist, which demonstrates the phase transition from CoMn<sub>2</sub>O<sub>4</sub> to Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> as a result of the surrounding carbon. From the XRD pattern of the CoMnO@CNTs/CNFs prepared at 800 °C, the previous CoMn<sub>2</sub>O<sub>4</sub> NPs are completely transformed to Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>. By increasing the temperature from 400 to 1000 °C, the CoMnO NPs evolved from CoMn<sub>2</sub>O<sub>4</sub> to oxygen-vacant Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> with separated metallic Mn<sub>3</sub>Co<sub>7</sub> at the surface. The reason for the formation of such a unique structure is that during the growth

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

DOI: 10.1039/C6EE03054H Journal Name

of CNTs under an Ar/NH<sub>3</sub> condition at 1000 °C, the as-formed  $CoMn_2O_4$  NPs were reduced to  $Co_2Mn_3O_8$  with a partial reduction of the metallic  $Mn_3Co_7$  on the surfaces surrounded by carbon shells; this reduction is required for the formation of the CNTs.



Figure 3 (a) XRD pattern of the CoMnO@CNTs/CNFs architecture prepared at different temperatures. The (b) Co 2p, (c) Mn 2p and (d) O 1s XPS spectra of (curve I) pre-oxidation  $CoMn_2O_4/CNFs$  prepared at 400 °C and (curve II) oxygen-deficient  $Mn_3Co_7$ - $Co_2Mn_3O_8@CNTs/CNFs$  prepared at 1000 °C.

The XPS spectra of the CoMn<sub>2</sub>O<sub>4</sub>/CNFs prepared at 400 °C and the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared at 1000 °C were obtained to further investigate the change in the surface chemical state (Figure 3). The XPS survey the CoMn<sub>2</sub>O<sub>4</sub>/CNFs and spectra of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs hybrids both exhibit C, N, O, Co and Mn elements (Figure S2 and S3). The C 1s spectrum of CoMn<sub>2</sub>O<sub>4</sub>/CNFs shows four peaks with the binding energies (BEs) at 284.6, 285.3, 286.7 and 288.9 eV, which corresponds to the -C-C/H, -C-N, -C-OH and -O=C-O functional groups, respectively (Figure S4).<sup>[25]</sup> The CoMn<sub>2</sub>O<sub>4</sub>/CNFs prepared at 400 °C exhibit abundant oxygen groups. For the oxygendeficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared at 1000 °C, the C 1s spectra (Figure S5) show three peaks with BEs at 284.7, 285.2 and 285.8 eV, corresponding to the sp<sup>2</sup>-hybridized graphitic carbon, -C-N and -C-OH/C=O groups, respectively.<sup>[26]</sup> Compared with that of the  $CoMn_2O_4/CNFs$  hybrid, the percentage of the oxygen groups of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs decreases significantly.

The Co 2p spectrum of CoMn<sub>2</sub>O<sub>4</sub>/CNFs (Figure 3b, curve I) includes two main peaks with BEs at 781.6 and 797.4 eV, corresponding to Co  $2p_{3/2}$  and  $2p_{1/2}$  of the Co<sup>2+</sup> ions. The satellite peaks for the Co<sup>2+</sup> ions are located at 786.6 and 802.9 eV, respectively, which is in agreement with the previous results in literature for spinel-type CoMn<sub>2</sub>O<sub>4</sub> crystals.<sup>[27]</sup> However, compared with those of CoMn<sub>2</sub>O<sub>4</sub>/CNFs, the main peaks in the Co 2p XPS spectra of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs (Figure 3b, curve II) move to lower BEs. Three main peaks with BEs at 778.6, 780.0 and 781.6 eV are attributed to Co  $2p_{3/2}$  for Co<sup>0</sup>, Co<sup>3+</sup> and Co<sup>2+</sup>, respectively, and another peak at 793.6 eV is mainly assigned to Co  $2p_{1/2}$  for Co<sup>0</sup>.<sup>[28]</sup> The shifting of the Co 2p region of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs to lower BEs can be attributed to the

surface reduction of the CoMn<sub>2</sub>O<sub>4</sub> by the surrounding carbon during the growth process of the CNTs. The appearance of the metallic Co (778.6 eV) confirms that there are amounts of metallic Co separated out from the spinel CoMn<sub>2</sub>O<sub>4</sub> and formed at the interface between the surrounding carbon and the surface of CoMn<sub>2</sub>O<sub>4</sub>. Because of the strong reduction ability of the carbon precursor at 1000 °C, the CoMn<sub>2</sub>O<sub>4</sub> NPs formed on the CNFs surfaces were converted into Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs with oxygen vacancies.



**Figure 4** FE-SEM and TEM images (a, b) of the CoMn<sub>2</sub>O<sub>4</sub>/CNFs prepared by pre-oxidation at 400 °C under atmospheric conditions, (c, d) CoMn<sub>2</sub>O<sub>4</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>/CNFs prepared by pre-oxidation and then graphitization at 600 °C under Ar/NH<sub>3</sub> conditions, (e, f) the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared by pre-oxidation and then graphitization at 800 °C under Ar/NH<sub>3</sub> conditions, and then graphitization at 800 °C under Ar/NH<sub>3</sub> conditions, and then graphitization at 800 °C under Ar/NH<sub>3</sub> conditions, and then graphitization at 1000 °C under Ar/NH<sub>3</sub> conditions.

The Mn 2p XPS spectra of the  $CoMn_2O_4/CNFs$  and  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$  are shown in Figure 3c. Three distinct spin-orbit peaks centered at 642.5, 653.9 and 646.3 eV are observed with a spin-energy separation of 11.4 eV, corresponding to the Mn  $2p_{3/2}$ , Mn  $2p_{1/2}$  and satellite peaks of the Mn (IV) state.<sup>[29]</sup> In addition, the Mn<sup>2+</sup> state is also present, as indicated by the existence of a less prominent peak at 641.2 eV. The Mn 2p XPS spectra of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs show the predominant peaks shifting to lower BEs, and the peaks for Mn  $2p_{3/2}$  and Mn  $2p_{1/2}$  of the Mn<sup>4+</sup> states shift to 643.3 and 653.4 eV a much weaker satellite peak of Mn<sup>4+</sup>. Therefore, the peaks of Mn<sup>4+</sup> for the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs indicate a different CoMn

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

oxide state with spin-energy separation of 10.1 eV, which is in the form of  $Co_2Mn_3O_8$  crystals. In addition, a new emerged peak located at 539.0 eV corresponds to the metallic  $Mn^{(0)}$  state, further demonstrating the existence of metallic Mn on the surface of  $Co_2Mn_3O_8$  NPs.

As shown in curve II in Figure 3c, the peak belonging to  $\mathrm{Mn}^{2*}$  shifts to 640.7 eV, which indicates the strong reduction of Mn from  $CoMn_2O_4$  to  $Co_2Mn_3O_8$  and the formation of metallic  $Mn_3Co_7$  on the  $Co_2Mn_3O_8$  surface caused by the reduction of the surrounding carbon.<sup>[31]</sup> The Mn/Co atomic ratio in the  $CoMn_2O_4/CNFs$  is 1.74, while the Mn/Co atomic ratio in the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>/CNTs/CNFs is reduced to 0.67, which indicates the phase transformation of CoMn oxides during the CNTs growth process. In addition, the Mn/Co ratio decreases from 1.74 to 0.67, which indicates that there amounts of metallic Mn<sub>3</sub>Co<sub>7</sub> separated out from the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> and formed at the surface between the  $Co_2Mn_3O_8$  NPs and carbon shell. The strong shifts of the Mn<sup>2+</sup> oxidation state of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs to lower BEs is inevitably due to the valence degeneracy and strong charge transfer from the surrounding carbon.  $^{\rm [32]}$  As is known, the BEs of Mn  $2p_{3/2}$  can increase by increasing its valence state. The reduction of CoMn<sub>2</sub>O<sub>4</sub> by the surrounding carbon in an Ar/NH<sub>3</sub> atmosphere at 1000 °C leads to a shift of the Mn 2p spectrum to lower BEs, which suggests a decrease in the valence state of Mn ions with oxygen vacancies.[33]

The shifts of the BEs in the Co 2p and Mn 2p XPS spectra are possibly related to the partial removal of oxygen from the lattice of CoMn<sub>2</sub>O<sub>4</sub>, and indeed, there is also a decrease in the atomic ratio [O]/[Co + Mn] from 3.97 to 2.55. This means that the reduction certainly leads to the formation of oxygen vacancies in the CoMn<sub>2</sub>O<sub>4</sub> structure. The O1s spectra (curve a, Figure 3d) of the  $CoMn_2O_4/CNFs$  contain four oxygen contributions. The BEs at 531.3, 531.9 and 532.5 eV are the characteristic peaks of hydroxyl groups and surface-adsorbed oxygen groups on the CNFs.<sup>[34]</sup> The other peak at 530.3 eV corresponds to the lattice oxygen in the metal oxide (metal-Ometal) of  $CoMn_2O_4$ .<sup>[35]</sup> The O 1s region of the  $Mn_3Co_7$ -Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs also shows four chemical states with BEs at 530.4, 531.5, 532.4 and 533.7 eV. The BE at 530.4 eV belongs to the oxygen of the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> nanocrystals. The others peaks with BEs at 531.5, 532.4 and 533.7 eV are assigned to the coordinatively unsaturated oxygen species, oxygen groups on the carbon surface and adsorbed water molecules.<sup>[36]</sup> The results from the O1s XPS spectra demonstrate that the surfaces of CNTs and CNFs possess some oxygen groups, which make the CNTs and CNFs hydrophilic. The results from XRD and XPS reveal the formation of oxygendeficient Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> nanostructures after the 1000 °C heating treatment.

Figure 4 shows the evolution of the morphologies of the CoMnO@CNTs/CNFs nanostructures prepared at different temperatures. Figure 4a and 4b display the FE-SEM and TEM images of the CoMn<sub>2</sub>O<sub>4</sub>/CNFs treated at 400 °C. Small CoMn<sub>2</sub>O<sub>4</sub> NPs are formed uniformly on the surfaces of pre-oxidized CNFs. The size of the CoMn<sub>2</sub>O<sub>4</sub> NPs ranges from 3 to 10 nm. The HRTEM image (the inset in Figure 4b) clearly shows the typical lattice distance of the (400) planes of CoMn<sub>2</sub>O<sub>4</sub>/CNFs were further graphitized under Ar/NH<sub>3</sub> conditions. Figure 4c

and 4d shows the morphology of the CoMnO/CNFs heated at 600 °C. We found that the CNFs became rough and porous as the size of CoMnO NPs (consisting of CoMn<sub>2</sub>O<sub>4</sub> and Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>, Figure 4c) increased. In addition, the CoMnO NPs were surrounded by several carbon layers, which resulted in the formation of CoMnO/carbon core/shell structures (Figure 4d). This occurred because the CoMnO NPs could catalyze the graphitization of the surrounding carbon during the graphitization process. It should be noted that the treatment at 600 °C only leads to the formation of CoMnO/carbon core/shell structures.



**Figure 5** HAADF-STEM and STEM-EDX mapping images (a, b) of the CoMn<sub>2</sub>O<sub>4</sub>/CNFs prepared by pre-oxidation at 400 °C under atmospheric conditions, (c, d) CoMn<sub>2</sub>O<sub>4</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>3</sub>/CNFs prepared by pre-oxidation and then graphitization at 600 °C under Ar/NH<sub>3</sub> conditions, (e, f) the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared by pre-oxidation and then graphitization at 800 °C under Ar/NH<sub>3</sub> conditions, and (g, h) the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared by pre-oxidation and then graphitization at 1000 °C under Ar/NH<sub>3</sub> conditions.

When the graphitization temperature increases to 800 °C, small CNTs with  $Co_2Mn_3O_8$  NPs located at their tips are vertically grown on porous CNFs (Figure 4e and 4f). The length of the CNTs grown ranges from 50 to 400 nm while the size of the encapsulated  $Co_2Mn_3O_8$  NPs ranges from 10 to 50 nm. Because of the high graphitization temperature, large amounts of the onion-like carbon are formed in the CNFs due to the

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

DOI: 10.1039/C6EE03054H Journal Name

catalytic effects of  $Co_2Mn_3O_8$  NPs. The encapsulated  $Co_2Mn_3O_8$ NPs are also surrounded by multilayer carbon, and the layers of carbon increase as the temperature increases. The HRTEM image (the inset in Figure 4f) illustrates that the interlayer distance of the surrounding carbon is 3.6 Å, which corresponds to the (002) planes of carbon. Upon increasing the temperature to 1000 °C, large amounts of CNTs were grown densely on the CNFs to form the CNT forest architectures. The length of the grown CNTs increases to hundreds of micrometers. The graphitic porous CNFs encapsulated with oxygen-deficient  $Mn_3Co_7$ - $Co_2Mn_3O_8$ /carbon core/shell and onion-like carbon structures were also obtained.

HAADF-STEM and STEM-EDX mapping images further confirmed the structure and morphology evolutions and CNT growth process. As shown in Figure 5a and 5b, the STEM-EDS mapping images show distinct nanofiber decorated with small nanoparticles. Figure 5b exhibits C, N, Co, Mn and O elements, demonstrating the formation of CoMn<sub>2</sub>O<sub>4</sub> NPs on O-rich CNFs. As shown in Figure 5c, the CoMnO/CNFs prepared at 600 °C display porous structures and the CoMnO nanoparticles were confirmed by the STEM-EDS mapping images (Figure 5d). As shown in the STEM mapping images (Figure 5e), the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs architectures consist of branched Ndoped CNTs with the encapsulated Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs at their tips and porous graphitic CNF hosts with some Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@carbon core-shell structures and onion-like carbon nanostructures. Notable, the STEM-EDS mapping images of oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs prepared at 1000 °C also indicate that the CoMnO NPs at the tips of the N-doped CNTs serve as the standard catalyst for the growth of CNTs.



Figure 6 (a) HER polarization curves and corresponding (b) Tafel slopes of the CoMnO@CNTs/CNFs catalysts prepared at different temperatures (400-1000 °C) and commercial Pt/C (20 wt %) catalysts in 0.5 M H<sub>2</sub>SO<sub>4</sub> solution. (c) The chronoamperometric responses at a constant potential of -0.20 V vs. RHE for the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs electrode (prepared at 1000 °C) and

commercial Pt/C catalysts. The inset in (c) is the photograph of the generation of H<sub>2</sub> bubbles on the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs membrane electrode. (d) OER polarization curves and corresponding (e) Tafel slopes of the COMnO@CNTs/CNFs catalysts prepared at different temperatures (400-1000 °C) and commercial IrO<sub>2</sub> (20 wt %) catalysts in 1 M KOH solution. The inset in (f) is the photograph of the generation of O<sub>2</sub> bubbles on the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs membrane electrode.

We also made individual Co oxides/CNFs and Mn oxides/CNFs hybrids under the same synthesis conditions. Here, no CNTs are observed on the CNFs, indicating that the individual Co or Mn oxide NPs cannot catalyze the growth of CNTs under the same conditions (Figure S6 and S7). Figure S8 confirms that the as-formed Co oxides on the CNFs consist of metallic Co and CoO nanocrystals, indicating the formation of Co oxide structures with oxygen vacancies during the heat treatment process. Similarly, the Mn oxides/CNFs also show the existence of Mn, MnO<sub>2</sub> and Mn<sub>3</sub>O<sub>4</sub> nanocrystals (Figure S9). Both the Co-CoO/CNFs and Mn-MnO<sub>x</sub>/CNFs have large amounts of fullerene-like graphitic carbon pores in their CNFs, which indicate that the individual oxygen-vacancy Co and Mn oxides can only catalyze the graphitization of CNFs without supporting the growth of CNTs. Therefore, the oxygendeficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs play an important role in the growth of CNTs and the graphitization of CNFs. The growth of CNTs begins with the phase transitions from CoMn<sub>2</sub>O<sub>4</sub> to Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>, and the oxygen-vacancy Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs with Mn<sub>3</sub>Co<sub>7</sub> on their surfaces can work well as catalysts for the growth of CNT forests. Due to catalytic effects of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs, the amorphous carbon can themselves form fullerene-like graphitic carbon layers surrounding the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs. Compared with the traditional metal catalysts for the growth of CNTs, the oxygen atoms in Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs can improve the capture of carbon species and consequently facilitate the growth of CNTs on the surface of Mn<sub>3</sub>Co<sub>7</sub>-Co2Mn3O8 NPs. These findings demonstrate a new kind of transition metal oxides catalyst for the growth of CNTs and also highlight the importance of oxygen in the growth of CNTs.

The HER and OER activity of the CoMnO/CNTs/CNFs were investigated to illustrate the structure-dependent behavior (Figure 6). The CoMn<sub>2</sub>O<sub>4</sub>/CNFs prepared at 400 °C without the CNTs growth show low HER activity with a  $\eta_{-10}$  value (the overpotential at a current density of -10 mA cm<sup>-2</sup>) of 343 mV and a high Tafel slope of 245 mV decade<sup>-1</sup>, which indicates the poor HER activity of the CoMn<sub>2</sub>O<sub>4</sub>/CNFs (Figure 6a and 6b). The CoMnO@CNTs/CNFs with small CNT tips (consisting of CoMn<sub>2</sub>O<sub>4</sub> and Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>) prepared at 600 °C exhibit a smaller  $\eta_{-10}$  value of 232 mV and a Tafel slope of 139 mV decade<sup>-1</sup> (Figure 6a and 6b). When the temperature increases further to 800 °C, the formed  $Co_2Mn_3O_8@CNTs/CNFs$  with small CNTs show a lower  $\eta_{-10}$  value of 218 mV and a Tafel slope of 136 mV decade<sup>-1</sup>, which demonstrates the improved HER activity (Figure 6a and 6b). The electrocatalytic parameters are summarized in Table 1. The oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs with CNT forests (prepared at 1000 °C) exhibit the lowest  $\eta_{-10}$  value of 175 mV and a Tafel slope of 98 mV decade<sup>-1</sup> (Figure 6a and 6b), indicating that the growth of CNTs and encapsulated oxygen-deficient Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs with separated Mn<sub>3</sub>Co<sub>7</sub> on their surfaces can greatly improve the HER activity. The electrocatalytic HER activity obtained is lower than that of recently reported transition metal oxide/carbon catalysts (Table S1).<sup>[37-39]</sup> The Nyquist plots of the

#### Journal Name

CoMnO@CNTs/CNFs catalysts with various morphologies are obtained in 0.5 M H<sub>2</sub>SO<sub>4</sub>, shown in Figure S10. The EIS results reveal dramatically decreased charge transfer resistance ( $R_{CT}$ ) for the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs (~12  $\Omega$ ), revealing its more facile electrode kinetics and faster diffusion rate of reactants for enhancing the catalytic activity (Figure S10). The 3D Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs membrane was further tailored into a 1 x 1 cm area and used directly as the electrode for the stability test. Figure 6c shows that the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs assmaller decrease (11.8 %) in the current density for HER under continuous operation for 10 h, whereas the Pt/C catalyst shows a relatively larger decrease (19.5 %) during the continuous operation for 10 h.



7 (a) CVs of the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Figure Co2Mn3O8@CNTs/CNFs catalyst (prepared at 1000 °C) in Ar- and O2saturated 0.1 M KOH. (b) ORR polarization curves of the oxygendeficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs and Pt/C (20 wt%) catalysts. (c) Tafel slopes of Pt/C (20 wt %) and Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs. (d)Polarization curves of oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs catalysts at different rotation rates. (e) The K-L plots of oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs catalysts at various potentials. (f) The chronoamperometric responses of the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs electrode and Pt/C catalysts for ORR.

The OER activity of the CoMnO@CNTs/CNFs prepared at temperatures from 400 to 1000 °C are shown in Figure 6d and 6e. With increased temperatures, the  $\eta_{10}$  values decrease from 591 to 374 mV and the Tafel slopes also decrease from 170 to decade<sup>-1</sup>. oxygen-deficient mV The 66 Mn<sub>2</sub>Co<sub>7</sub>- $Co_2Mn_3O_8@CNTs/CNFs$  prepared at 1000 °C display a  $\eta_{10}$  value of only 374 mV, which is over 160 mV lower than that of IrO<sub>2</sub> catalysts (1.633 V,  $\eta_{10}$ = 403 mV). The OER activity achieved by the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs compares favorably to that of recently reported OER catalysts, N-Fe-CNT<sup>[25]</sup>, Mn-Co/CNT<sup>[40]</sup>, CP/CTs/Co-S<sup>[41]</sup>, including

 $Co@Co_3O_4$ -CNTs<sup>[16]</sup>, NiFe LDH<sup>[42]</sup>, and  $La_{0.8}Sr_{0.2}MnO_{3-\delta}$ <sup>[43]</sup> (Table S2). The Tafel slope of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs is only 66 mV decade<sup>-1</sup>, which is lower than that of IrO<sub>2</sub> (78 mV decade<sup>-1</sup>), further confirming the superior OER performance. The Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs electrode is very stable under continuous operation for 10 h, while the IrO<sub>2</sub> catalyst displays a continuous loss in the current density during the OER operation (Figure 6f). The results indicate that the change in temperature leads to the evolution of the morphology and structure of the CoMnO@CNTs/CNFs, and the oxygen-deficient structures exhibit enhanced OER and HER activity. Figure S11 displays the morphologies and structures of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs electrode after continuously stability tests for HER and OER, respectively. The electrocatalysts can still keep the 3D architectures with branched CNTs and the  $Mn_3Co_7\mathchar`-Co_2Mn_3O_8$  did not dissolved in the acid or alkaline solution due to the protection of carbon shells in CNTs and CNFs, indicating their superior stability.

View Article Online DOI: 10.1039/C6EE03054H

ARTICLE

Based on these exciting OER results, the ORR activity of the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs was also determined. As shown in Figure 7a, a well-defined cathodic peak is clearly observed at ~0.81 V for the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs in O<sub>2</sub>-saturated 0.1 M KOH solution while no redox peaks were observed in Ar-saturated 0.1 M KOH solution, indicating their excellent ORR activity. The LSV of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs exhibits a half-wave potential (E<sub>1/2</sub>) of 0.82 V for ORR (Figure 7b), which is better than that of Pt/C (0.81 V). The Tafel slope of the Mn<sub>3</sub>Co<sub>7</sub>-Co2Mn3O8@CNTs/CNFs is 70 mV decade<sup>-1</sup>, which is close to that of the Pt/C catalyst (70 mV decade $^{-1}$ ) and indicates their excellent electrocatalytic activity for ORR. The LSVs of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs were further recorded at different rotating rates from 400 rpm to 3200 rpm (Figure 7d). The electron-transfer numbers (n) of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs at different potentials are analyzed by the slopes of the linearly fitted Koutecky-Levich (K-L) plots using the K-L equation. The K-L plots exhibit first-order reaction kinetics with regards to the concentration of dissolved oxygen at various potentials (Figure 7e). The value of n is calculated to be in the range of 3.41-3.73, which is close to the theoretical value of 4.00 for Pt/C and indicates a high selectivity for the four-electron-dominated ORR pathway. The ORR activity of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs was also compared with those of recently reported state-of-art catalysts (Table S3), further revealing their excellent ORR electrocatalytic performance. The stability test results (Figure 7f) indicate that the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs catalyst is very stable for the ORR (85.3 % of current density remain) under continuous operation for more than 10 h, whereas the Pt/C exhibits a continuous current loss (54.2 % of the initial current density remains) during the continuous operation.  $\mu$ 

The oxygen-deficient  $Co_2Mn_3O_8@CNTs/CNFs$  with metallic  $Mn_3Co_7$  on the  $Co_2Mn_3O_8$  surfaces exhibit excellent electrocatalytic activity and good stability for HER, OER and ORR. The integration of 1D CNTs, 1D CNFs and OD oxygen-deficient  $Mn_3Co_7$ - $Co_2Mn_3O_8$  along with their synergetic effect are vital for improving the kinetics of ORR, OER and HER. (a) Small  $Mn_3Co_7$  alloy NPs are formed at the interfaces between the  $Co_2Mn_3O_8$  NPs and carbon shells. The oxygen vacancies can enhance the electron mobility and make the  $Co_2Mn_3O_8$  NPs easily accessible to  $O_2$ , which enables them to serve as

active sites for ORR and OER. The large amounts of  $O_2$ adsorbed by the oxygen vacancies in the Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs can react directly with the separated  $\mathsf{Mn}_3\mathsf{Co}_7$  on the surfaces to form strong metal- $\mathsf{O}_2$  bonds, which leads to the elongation of the O-O bond and lowers the  $\mathsf{O}_2$ reduction barrier.<sup>[43-49]</sup> Therefore, by promoting the partial dissociation of metallic Mn<sub>3</sub>Co<sub>7</sub> to form CoMn oxides and exposing more Mn/Co active centers, the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs lead to a highly efficient ORR and OER activity. (b) During the HER process, the metallic Mn<sub>3</sub>Co<sub>7</sub> on the surfaces can lower the free energy of adsorption of the oxides for hydrogen ions and enhance the hydrogen adsorption, which results in the low overpotential values. The 3D framework structures and oxygen-deficient Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> can lower the gas desorption energy barrier for higher HER activity. (c) The surrounding carbon shells not only improve the conductivity of Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs but they also stabilize the oxygen vacancies during the electrocatalysis process. Moreover, the branched CNTs grown on CNFs possess a 3D hierarchical porous structure and high surface area, which facilitates the diffusion of active species and enhances the mass transport during the electrocatalytic process. The unique 3D hierarchical framework structure formed by the

interconnected CNTs provides excellent conductivity, stability and smooth pathways to facilitate the penetration of electrolytes and enlarge the contact surface between reactants and active sites. (d) Furthermore, the 3D hierarchical structure formed by the 1D CNTs and CNFs enables a facile release of evolved gas bubbles to further improve the reaction kinetics of the ORR, OER and HER. The surrounding carbon shells of the CoMnO NPs provide remarkable corrosion resistance in a harsh operating environment. Benefiting from the synergistic effects of the unique 3D hierarchical structures, the excellent conductivity of the CNTs and CNFs, and the oxygen vacancy structures of the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub> NPs, the Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs work as highly efficient electrocatalysts for oxygen reduction reaction and water splitting. In addition, this strategy can be applied for constructing other organic materials. As shown in Figure S12, the silk fiber can be also used as the fiber reactor to grow the CNTs with the CoMnO as catalysts, leading to the formation of 3D nanoarchitecture. The silk derived carbon fibers are densely covered by branched CNTs without any additional carbon resources. This work demonstrates a novel integration-andmarriage concept for developing superior catalysts for electrochemical energy devices.

Table 1 Comparisons of HER, OER and ORR activity among various catalysts.

Reactions		Catalysts					
		CoMn <sub>2</sub> O <sub>4</sub> /CNFs (400 °C)	CoMn <sub>2</sub> O <sub>4</sub> - Co <sub>2</sub> Mn <sub>3</sub> O <sub>8</sub> /CNFs (600 °C)	Co <sub>2</sub> Mn <sub>3</sub> O <sub>8</sub> @CNT s/CNFs (800 °C)	Mn <sub>3</sub> Co <sub>7</sub> - Co <sub>2</sub> Mn <sub>3</sub> O <sub>8</sub> @CNTs/CN Fs (1000 <sup>°</sup> C)	Pt/C	IrO <sub>2</sub>
HER	η at 10 mA cm <sup>-2</sup> (mV)	345	233	220	176	30	-
	Tafel slope (mV dec⁻¹)	245	139	136	98	35	-
OER	η at 10 mA cm <sup>-2</sup> (mV)	577	447	410	374	-	404
	Tafel slope (mV dec <sup>-1</sup> )	170	103	84	66	-	78
ORR	Onset Potential (V)	-	-	-	0.89	0.87	-
	Tafel slope(mV dec <sup>-1</sup> )	-	-	-	70	70	-

Published on 01 December 2016. Downloaded by Washington University in St. Louis on 02/12/2016 07:17:49

#### Conclusions

In summary, by starting with the PAN nanofibers containing Co-Mn salts as the precursor, we report an effective strategy for the rational design and construction of 3D framework architectures based on the integration of 0D oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8$  NPs, 1D N-doped CNTs and 1D graphitic porous CNFs. The optimized 3D nanostructure exhibits superior electrocatalytic activity and stability for ORR, OER and HER. The remarkable electrochemical properties are mainly attributed to the synergistic effects obtained from the engineering of oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8$  with exposed active sites and the 3D hierarchical porous structure, which consists of branched CNTs and interconnected CNFs. This work demonstrates a novel integration-and-marriage concept for developing superior catalysts for electrochemical energy devices.

#### Experimental

Fabrication of 3D oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs architecture.

In a typical procedure, 0.15 g  $Co(NO_3)_2$  and 0.15 g  $Mn(CH_3COO)_2$  were firstly dissolved in 13.5 g N,Ndimethylformamide (DMF) solution containing 10 wt% PAN, and then stirred for 10 h to get a homogeneous solution. The homogeneous solution was immediately transferred into a plastic syringe attached to a 23 gauge needle that was electrically connected to a high voltage power supply. The applied voltage was 10 kV, the needle-to-collector distance

#### Journal Name

View Article Online DOI: 10.1039/C6EE03054H ARTICLE

was 15 cm, and the flow rate of the solution was 0.6 mL/h. The electrospun nanofibrous membrane were carefully detached from the home-built collector, and then dried at 80 °C for 3 h in an oven to vaporize the residual solvent. The direct growth of the  $Mn_3Co_7-Co_2Mn_3O_8@CNTs/CNFs$  hybrid was carried out in a home-built chemical vapor deposition (CVD) furnace. The as-collected Co-Mn-PAN precursor nanofibrous membrane was placed in a ceramic boat located at the center of the heating zone of the furnace. The Co-Mo-PAN precursor nanofibrous membrane were firstly heated to 400 °C in air at a rate of 5 °C/min and maintained for 6 h for stabilization. Then, the furnace was heated up to 1000 °C at a rate of 5 °C/min and maintained under  $Ar/NH_3$  condition for 6 h.

#### Materials characterizations

Field emission scanning electron microscopy (FE-SEM) images were characterized by a JSM-6700F FE-SEM (JEOL, Japan) at an accelerating voltage of 3 kV. Transmission electron microscopy (TEM) images were taken using a JSM-2100 transmission electron microscope (JEOL, Japan) at an accelerating voltage of 200 kV. The high-angle annular dark field scanning transmission electron microscopy (HAADF-STEM) images, STEM mapping, and line-scan energy dispersive X-ray spectroscopy (EDX) were recorded using a STEM (Tecnai G2 F30S-Twin, Philips-FEI) at an accelerating voltage of 300 kV. Xray diffraction (XRD) patterns were analyzed using a Bruker AXS D8 DISCOVER X-ray diffractometer with Cu  $K_{\alpha}$  radiation ( $\lambda$ = 1.5406 Å) at a scanning rate of 0.02  $2\theta \text{ s}^{-1}$  in the  $2\theta$  range of 10-80°. X-ray photoelectron spectra (XPS) of the products were recorded using an X-ray photoelectron spectrometer (Kratos Axis Ultra DLD) with an Al (mono)  $K_{\alpha}$  source (1486.6 eV). The Al Kα source was operated at 15 kV and 10 mA.

#### Electrochemical characterization

The electrochemical experiments were performed in a threeelectrode cell at 25 °C. The graphite rod was used as a counter electrode. The saturated calomel electrode (SCE) and Hg/HgO (1 M KOH) electrodes served as the reference electrodes for the 0.5 M H<sub>2</sub>SO<sub>4</sub> and 1 M KOH electrolytes, respectively. The polarization curves were obtained at the sweep rate of 2 mV s after the initial cyclic voltammograms (CVs) (Autolab potentiostat/galvanostat (Model PGSTAT302N) workstation) for 1000 cycles at the scan rate of 100 mV s<sup>-1</sup> between 0 and 1.20 V vs reversible hydrogen electrode (RHE). The potentials were referenced to RHE by adding a value of (0.244 + 0.059 pH) V for SCE and (0.99 + 0.059 pH) for Hg/HgO (1 M KOH). The Ohmic potential drop (iR) losses that arise from the solution resistance were all corrected. Tafel plots were recorded with the linear portions at low overpotential fitted to the Tafel equation ( $\eta = a + b \log j$ , where  $\eta$  is the overpotential, *j* is the cathodic current density, and b is the Tafel slope).

The catalyst ink was prepared by dispersing 3 mg catalyst in 1 mL isopropanol/water solution (75/25 volumetric ratio). Next, 25  $\mu$ L Nafion solution (5 wt %) was added to the ink as a proton conducting binder to ensure good adhesion onto the electrode. The catalyst ink was ultrasonicated for 30 min to generate a homogeneous ink. 5  $\mu$ L of catalyst ink was transferred onto a glassy carbon electrode ( $\Phi$  3 mm) that was previously buff polished using a suspension of alumina. The catalyst loading amount on the working electrode was 215  $\mu$ g cm<sup>-2</sup>. The polarization curves were obtained at the sweep rate of 2 mV s<sup>-1</sup> after the initial cyclic voltammograms for 1000 cycles at the scan rate of 100 mV s<sup>-1</sup> between 0 and 1.20 V vs RHE. The EIS was carried out in a potentiostatic mode in the frequency range of  $10^5$  to 0.1 Hz with the amplitude of 10 mV at -0.25 V vs RHE in 0.5 M H<sub>2</sub>SO<sub>4</sub>. The stability test of the oxygen-deficient Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs were also used the typical three-electrode system. The Mn<sub>3</sub>Co<sub>7</sub>-Co<sub>2</sub>Mn<sub>3</sub>O<sub>8</sub>@CNTs/CNFs membrane was tailored into a neat square (1×1 cm) and directly utilized as the working electrode in 0.5 M H<sub>2</sub>SO<sub>4</sub> and 1 M KOH electrolytes. The CV profiles were obtained in N<sub>2</sub>- or O<sub>2</sub>-saturated 0.1 M KOH solution at the scan rate of 20 mVs<sup>-1</sup>. The RDE tests for ORR are measured in O<sub>2</sub>-saturated 0.1 M KOH solution rates at the scan rate of 10 mVs<sup>-1</sup>.

#### Acknowledgements

The authors gratefully acknowledge the financial support from the National Natural Science Foundation of China (51373154, 51472182, 21571112, 51372125 and 51671003), the National Key Research and Development Program of China (No. 2016YFB0100201), the start-up supports from Peking University, Young Thousand Talented Program, the Program for Innovative Research Team of Zhejiang Sci-Tech University, and the 521 Talent Project of Zhejiang Sci-Tech University.

#### Notes and references

- J. Luo, J. H. Im, M. T. Mayer, M. Schreier, M. K. Nazeeruddin, N. G. Park, S. D. Tilley, H. J. Fan and M. Grätzel, *Science*, 2014, **345**, 1593-1596.
- 2 C. Liu, B. C. Colón, M. Ziesack, P. A. Silver and D. G. Nocera, *Science*, 2016, **352**, 1210-1213.
- 3 M. J. Kenney, M. Gong, Y. Li, J. Z. Wu, J. Feng, M. Lanza and H. Dai, *Science*, 2013, **342**, 836-840.
- 4 J. Zhang, Z. Xia and L. Dai, *Sci. Adv.*, 2015, **1**, e1500564.
- 5 B. Zhang, X. Zheng, O. Voznyy, R. Comin, M. Bajdich, M. García-Melchor, L. Han, J. Xu, M. Liu, L. Zheng, F. P. G. de Arquer, C. T. Dinh, F. Fan, M. Yuan, E. Yassitepe, N. Chen, T. Regier, P. Liu, Y. Li, P. D. Luna1, A. Janmohamed, H. L. Xin, H. Yang, A. Vojvodic and E. H. Sargent, *Science*, 2016, **352**, 333-337.
- 6 L. Bu, S. Guo, X. Zhang, X. Shen, D. Su, G. Lu, X. Zhu, J. Yao, J. Guo and X. Huang, *Nat. Commun.*, 2016, 7, 11850.
- 7 J. Zhang, Z. Zhao, Z. Xia and L. Dai, *Nat. Nanotechnol.*, 2015, **10**, 444-452.
- 8 J. Suntivich, H. A. Gasteiger, N. Yabuuchi, H. Nakanishi, J. B. Goodenough and Y. Shao-Horn, *Nat. Chem.*, 2011, **3**, 546-550.
- 9 H. B. Yang, J. Miao, S. F. Hung, J. Chen, H. B. Tao, X. Wang, L. Zhang, R. Chen, J. Gao, H. M. Chen, L. Dai and B. Liu, *Sci. Adv.*, 2016, **2**, e1501122.
- 10 J. Miao, F. X. Xiao, H. B. Yang, S. Y. Khoo, J. Chen, Z. Fan, Y. Y. Hsu, H. M. Chen, H. Zhang and B. Liu, *Sci. Adv.*, 2015, 1, e1500259.
- H. Fei, J. Dong, M. J. Arellano-Jiménez, G. Ye, N. D. Kim, E. L.G. Samuel, Z. Peng, Z. Zhu, F. Qin, J. Bao, M. J. Yacaman, P. M. Ajayan, D. Chen and J. M. Tour, *Nat. Commun.*, 2015, 6, 8668.
- H. Zhu, J. Zhang, R. Yanzhang, M. Du, Q. Wang, G. Gao, J. Wu,
  G. Wu, M. Zhang, B. Liu, J. Yao and X. Zhang, *Adv. Mater.*, 2015, 27, 4752-4759.
- 13 H. Lin, N. Liu, Z. Shi, Y. Guo, Y. Tang and Q. Gao, Adv. Funct. Mater., 2016, DOI: 10.1002/adfm.201600915.

DOI: 10.1039/C6EE03054H

Journal Name

- 14 V. W. Lau, I. Moudrakovski, T. Botari, S. Weinberger, M. B. Mesch, V. Duppel, J. Senker, V. Blum and B. V. L. Lau, *Nat Commun.*, 2016, 7, 12165.
- 15 D. Li, H. Baydoun, C. N. Verani and S. L. Brock, J. Am. Chem. Soc., 2016, 138, 4006-4009.
- 16 A. Aijaz, J. Masa, C. Rçsler, W. Xia, P. Weide, A. J. R. Botz, R. A. Fischer, W. Schuhmann and M. Muhler, *Angew. Chem. Int. Ed.*, 2016, **55**, 4087-4091.
- 17 B. Y. Xia, Y. Yan, N. Li, H. B. Wu, X. W. Lou and X. Wang, Nat. Energy, 2016, 1, 15006.
- 18 R. Gao, Z. Li, X. Zhang, J. Zhang, Z. Hu and X. Liu, ACS Catal., 2015, 6, 400-406.
- 19 T. Xu, T. Shimada, Y. Araki and J. Wang, *Nano Lett.*, 2015, **16**, 454-458.
- 20 R. Wu, J. Zhang, Y. Shi, D. Liu and B. Zhang, J. Am. Chem. Soc., 2015, 137, 6983-6986.
- Y. Shen, L. Yan, H. Song, J. Yang, G. Yang, X. Chen, J. Zhou, Z.
  Yu and S. Yang, *Angew. Chem. Int. Ed.*, 2012, **51**, 12202-12205.
- 22 W. Yang, X. Liu, X. Yue, J. Jia and S. Guo, J. Am. Chem. Soc., 2015, 137, 1436-1439.
- 23 K. N. Jung, S. M. Hwang, M. S. Park, K. J. Kim, J. G. Kim, S. X. Dou, J. H. Kim and J. W. Lee, *Sci Rep.*, 2015, **5**, 7665.
- 24 H. Yan, C. F. Blanford, W. H. Smyrl and A. Stein, *Chem Commun.*, 2000, **16**, 1477-1478.
- 25 H. T. Chung, J. H. Won and P. Zelenay, *Nat. Commun.*, 2013, 4, 1922.
- 26 Y. Qiu, G. Li, Y. Hou, Z. Pan, H. Li, W. Li, M. Liu, F. Ye, X. Yang and Y. Zhang, *Chem. Mater.*, 2015, **27**, 1194-1200.
- 27 J. Kang, A. Hirata, L. Chen, S. Zhu, T. Fujita and M. Chen, *Angew. Chem. Int. Ed.*, 2015, **54**, 8100-8104.
- 28 Y. J. Cho, C. H. Kim, H. S. Kim, W. S. Lee, S. H. Park and J. Park, *Chem. Mater.*, 2008, **20**, 4694-4702.
- 29 J. Masa, W. Xia, I. Sinev, A. Zhao, Z. Sun, S. Grützke, P. Weide, M. Muhler and W. Schuhmann, *Angew. Chem. Int. Ed.*, 2014, 53, 8508-8512.
- 30 X. Ge, Y. Liu, F. W. T. Goh, T. S. A. Hor, Y. Zong, P. Xiao, Z. Zhang, S. H. Lim, B. Li, X. Wang and Z. Liu, ACS Appl. Mater. Interfaces, 2014, 6, 12684-12691.
- 31 M. Ghiasi, M. U. Delgado-Jaime, A. Malekzadeh, R. P. Wang, P. S. Miedema, M. Beye and F. M. F. de Groot, *J. Phys. Chem. C*, 2016, **120**, 8167-8174.
- 32 J. Duan, S. Chen, S. Dai and S. Qiao, *Adv. Funct. Mater.*, 2014, 24, 2072-2078.
- 33 D. Jeong, K. Jin, S. E. Jerng, H. Seo, D. Kim, S. H. Nahm, S. H. Kim and K. T. Nam, ACS Catal., 2015, 5, 4624-4628.
- 34 Y. Zhu, W. Zhou, J. Yu, Y. Chen, M. Liu and Z. Shao, Chem. Mater., 2016, 28, 1691-1697.
- 35 E. McCalla, A. M. Abakumov, M. Saubanère, D. Foix, E. J. Berg, G. Rousse, M. L. Doublet, D. Gonbeau, P. Novák, G. V. Tendeloo, R. Dominko and J. M. Tarascon, *Science*, 2015, 350, 1516-1521.
- 36 S. Chen, J. Duan, M. Jaroniec, S. Qiao, Adv. Mater., 2014, 26, 2925-2930.
- 37 Z. L. Wang, X. F. Hao, Z. Jiang, X. P. Sun, D. Xu, J. Wang, H. X. Zhong, F. L. Meng and X. B. Zhang, *J. Am. Chem. Soc.*, 2015, 137, 15070-15073.
- 38 X. Xu, Y. Chen, W. Zhou, Z. Zhu, C. Su, M. Liu and Z. Shao, Adv. Mater., 2016, DOI: 10.1002/adma.201600005.
- 39 R. Subbaraman, D. Tripkovic, K.C. Chang, D. Strmcnik, A. P. Paulikas, P. Hirunsit, M. Chan, J. Greeley, V. Stamenkovic and N. M. Markovic, *Nat. Mater.*, **2012**, 11, 550-557.
- 40 A. Zhao, J. Masa, W. Xia, A. Maljusch, M. G. Willinger, G. Clavel, K. Xie, R. Schlögl, W. Schuhmann and M. Muhler, J. Am. Chem. Soc., 2014, 136, 7551-7554.
- 41 J. Wang, H. Zhong, Z. Wang, F. Meng, X. Zhang, ACS Nano, 2016, 10, 2342-2348.

- 42 M. Gong, Y. Li, H. Wang, Y. Liang, J. Z. Wu, J. Zhou, J. Wang, T. Regier, F. Wei and H. Dai, J. Am. Chem. Soc., 2013, 135, 8452-8455.
- 43 M. Risch, K. A. Stoerzinger, S. Maruyama, W. T. Hong, I. Takeuchi and Y. Shao-Horn, *J. Am. Chem. Soc.*, 2014, **136**, 5229-5232.
- 44 T. Y. Ma, Y. Zheng, S. Dai, M. Jaroniec and S. Z. Qiao, J. Mater. Chem. A, 2014, **2**, 8676-8682.
- 45 Q. Zhang, Z. Li, S. Wang, R. Li, X. Zhang, Z. Liang, H. Han, S. Liao and C. Li, *ACS Catal.*, 2016, **6**, 2182-2191.
- 46 F. M. Toma, A. Sartorel, M. Iurlo, M. Carraro, P. Parisse, C. Maccato, S. Rapino, B. R. Gonzalez, H. Amenitsch, T. D. Ros, L. Casalis, A. Goldoni, M. Marcaccio, G. Scorrano, G. Scoles, F. Paolucci, M. Prato and M. Bonchio, *Nat. Chem.*, 2010, 2, 826-831.
- 47 H. B. Tao, L. Fang, J. Chen, H. B. Yang, J. Gao, J. Miao, S. Chen and B. Liu, J. Am. Chem. Soc., 2016, **138**, 9978-9985.
- 48 M. A. Ha, A. N. Alexandrova, J. Chem. Theory Comput., 2016, 12, 2889-2895.
- 49 H. A. Tahini, X. Tan, U. Schwingenschlögl, S. C. Smith, ACS Catal., 2016, 6, 5565-5570.



An effective strategy for the rational design of three-dimensional architectures for superior electrocatalysis through the integration of carbon nanofibers, carbon nanotubes and oxygen-deficient  $Mn_3Co_7-Co_2Mn_3O_8$  nanoparticles have been demonstrated.